



FINISHED GRADE:

- REFER TO PLANS FOR MATERIAL
- SET ELEVATION 13mm BELOW EDGE OF PATHWAY TO PREVENT PONDING

ASPHALT PAVING:

- HL-3 ASPHALT SURFACE COURSE, 40mm COMPACTED DEPTH
- HL-8 ASPHALT BINDER COURSE, 50mm COMPACTED DEPTH
- EDGES TO BE TAMPED AT A 45° ANGLE

GRANULAR 'A' OR 19mm Ø CRUSHER RUN LIMESTONE:

- MIN 150mm DEPTH
- EXTEND 300 mm BEYOND EDGE OF PAVING
- COMPACTED TO 100% S.P.M.D.D. MIN.

GRANULAR 'B':

- MIN 300mm DEPTH
- EXTEND 300 mm BEYOND EDGE OF PAVING
- COMPACTED TO 100% S.P.M.D.D. MIN.

GEOTEXTILE OR GEO-GRID:

- IF RECOMMENDED, PER GEOTECHNICAL

SUB-GRADE:

- TO BE PROOF-ROLLED
- REMOVE ANY INCOMPACTABLE MATERIAL AND REPLACE WITH APPROVED GRANULAR MATERIALS
- COMPACT SUB-GRADE TO 98% S.P.M.D.D. MIN.

NOTE:

1. REFER TO PLANS FOR PROPOSED ASPHALT WIDTH AND GRADING.
2. PONDING ON ASPHALT PAVING WILL NOT BE ACCEPTED.
3. ENSURE POSITIVE DRAINAGE ON ASPHALT SURFACE. WATER MUST NOT BE COLLECTED AND CONVEYED ALONG ASPHALT SURFACE.
4. DO NOT BACKFILL AGAINST ASPHALT MINIMUM 48 HOURS UNTIL ASPHALT HAS CURED.
5. REPAIR AND RESTORE ANY DAMAGE TO EXISTING CONDITIONS.
6. DETAIL TO BE READ IN CONJUNCTION WITH GEOTECHNICAL REPORT AND ADJUSTED PER RECOMMENDATIONS.
7. DETAIL TO BE READ IN CONJUNCTION WITH SPECIFICATIONS.
8. ALL MEASUREMENTS ARE IN MILLIMETERS UNLESS STATED OTHERWISE.